

CSM Reinforced Rubber Sheet-EX

Chloro-Sulfonated polyethylene Reinforced Rubber Sheet



Fire Retardant
Reinforced Rubber Sheet CSM(Gray/White) 0.7 EX



Fire Retardant
Reinforced Rubber Sheet CSM 2.0 EX

■ Phthalates-Free

【Advantages】

- Certified flame-retardant material for rail car at Japan.
- Superior in ozone and aging resistance.
- Superior in thickness precision due to calendar sheeting.

【Constitution and Materials】



Rubber	Chloro-Sulfonated Polyethylene
Fabric	Nylon
Surface	Both faces embossed

【Specifications】

Article Name	Thickness (mm)	Width (mm)	Length (m)	Weight (kg/m ²)	Tensile Strength (kN/m)	Elongation (%)	Tear Resistance (N)	Rubbing Test 9.8N×1000times
Fire Retardant Reinforced Rubber Sheet CSM (Gray/White)0.7 EX	0.7	1100	25	0.86	Longitudinal 70	Longitudinal 18	Longitudinal 340	No apparent abnormalities
					Transverse 66	Transverse 24	Transverse 455	
Fire Retardant Reinforced Rubber Sheet CSM 2.0EX	2.0	1120	10	2.86	Longitudinal 216	Longitudinal 29	Longitudinal 600	No apparent abnormalities
					Transverse 172	Transverse 36	Transverse 560	

※Specifications are subject to change without notice for improvement.

※The above mentioned value of properties is measured value and it is not guaranteed value.

【Example of Use】

- Canvas cover at connection of rail car
- Medium Flexible Joint

SHIBATA INDUSTRIAL CO.,LTD RUBBER SHEET DIVISION

Kobe : TEL.078(362)6030 FAX.078(362)6094
Tokyo : TEL.03(3292)3868 FAX.03(3292)3869