

受衝板付防舷材 CSS型
性能

規格	ゴム質	反力 (kN)	吸収エネルギー (kN・m)	規格	ゴム質	反力 (kN)	吸収エネルギー (kN・m)
CSS-300H	CRH	72.8	9.63	CSS-1150H	CRH	1070	541
	CR0	66.2	8.75		CR0	973	492
	CR1	58.7	7.76		CR1	863	437
	CR2	51	6.73		CR2	749	379
	CR3	39.2	5.18		CR3	576	291
	CR4	31.3	4.14		CR4	461	233
	CR5	23.5	3.11		CR5	346	175
CSS-500H	CRH	202	44.6	CSS-1250H	CRH	1270	696
	CR0	184	40.5		CR0	1150	633
	CR1	163	35.9		CR1	1020	561
	CR2	141	31.1		CR2	884	487
	CR3	109	23.9		CR3	680	374
	CR4	87.1	19.1		CR4	544	299
	CR5	65.3	14.3		CR5	408	224
CSS-630H	CRH	321	89.1	CSS-1450H	CRH	1710	1090
	CR0	292	81.0		CR0	1550	991
	CR1	259	71.8		CR1	1370	876
	CR2	225	62.3		CR2	1190	759
	CR3	173	47.9		CR3	915	584
	CR4	138	38.3		CR4	732	467
	CR5	104	28.7		CR5	549	350
CSS-800H	CRH	518	183	CSS-1600H	CRH	2070	1450
	CR0	471	166		CR0	1880	1320
	CR1	418	147		CR1	1670	1180
	CR2	362	128		CR2	1450	1020
	CR3	279	98.1		CR3	1120	785
	CR4	223	78.5		CR4	892	628
	CR5	167	58.9		CR5	669	471
CSS-1000H	CRH	810	356	CSS-2000H	CRH	3230	2850
	CR0	736	324		CR0	2940	2590
	CR1	653	287		CR1	2610	2300
	CR2	566	249		CR2	2260	1990
	CR3	436	191		CR3	1740	1530
	CR4	348	153		CR4	1390	1230
	CR5	261	115		CR5	1040	923

※ 設計変位量 52.5%
※ 性能公差 反力 ： +10%以下、吸収エネルギー ： -10%以上