

受衝板付超高性能防舷材 SPC型

性能

規格	ゴム質	反力 (kN)	吸収エネルギー (kN・m)	規格	ゴム質	反力 (kN)	吸収エネルギー (kN・m)
SPC-300H	SRH	125	19.6	SPC-1100H	SRH	1680	966
	SR0	112	17.6		SR0	1510	868
	SR1	92.7	14.6		SR1	1250	718
	SR2	82.4	13		SR2	1110	638
	SR3	71.5	11.3		SR3	963	554
	SR4	57.2	9		SR4	770	443
	SR5	34.3	5.4		SR5	462	266
SPC-600H	SRH	499	157	SPC-1150H	SRH	1830	1100
	SR0	449	141		SR0	1650	993
	SR1	371	117		SR1	1360	820
	SR2	330	104		SR2	1210	729
	SR3	286	89.9		SR3	1050	633
	SR4	229	71.9		SR4	841	506
	SR5	137	43.1		SR5	505	304
SPC-700H	SRH	680	249	SPC-1200H	SRH	2000	1250
	SR0	612	223		SR0	1800	1130
	SR1	505	185		SR1	1480	932
	SR2	449	164		SR2	1320	828
	SR3	390	143		SR3	1150	719
	SR4	312	114		SR4	916	575
	SR5	187	68.4		SR5	550	345
SPC-800H	SRH	887	371	SPC-1300H	SRH	2330	1600
	SR0	798	334		SR0	2100	1430
	SR1	659	276		SR1	1730	1190
	SR2	586	246		SR2	1540	1050
	SR3	509	213		SR3	1340	915
	SR4	407	170		SR4	1070	732
	SR5	244	102		SR5	642	439
SPC-900H	SRH	1120	530	SPC-1450H	SRH	2920	2220
	SR0	1010	476		SR0	2630	1990
	SR1	835	393		SR1	2170	1640
	SR2	742	350		SR2	1930	1460
	SR3	644	303		SR3	1670	1270
	SR4	515	243		SR4	1340	1020
	SR5	309	146		SR5	804	612
SPC-1000H	SRH	1390	726				
	SR0	1250	653				
	SR1	1030	539				
	SR2	916	480				
	SR3	795	416				
	SR4	636	333				
	SR5	382	200				

※ 設計変位置量 70%

※ 性能公差 反力 ： +10%以下、吸収エネルギー ： -10%以上